

## **Declaration of Performance**

UKCA - UGP140 - 01

1. Product Type Solar Grade Celcon Plus Blocks

2. Product identification UGP140

3. Intended use Load bearing and non-load bearing applications in all forms of walling

including single leaf, cavity, partitions, retaining and basements

4. Manufacturer H+H UK Ltd, Celcon House, Ightham, Sevenoaks, Kent, TN15 9HZ

Tel: +44 1732 880333 Email: info@hhcelcon.co.uk

5. System AVCP 2+

6. UK Designated Standard BS EN 771-4:2011 + A1:2015

7. UK Approved Body British Board of Agrément, PO Box 195, Bucknalls Lane, Garston, Watford, Herts WD25 7NG

(Approved Body reference N° 0836)

8. Declared Performance

| Essential characteristics                               |            | Performance                             |
|---|------------|---|
| Dimensions  | length, mm | 630                                     |
|   | height, mm | 215                                     |
|   | width, mm  | 140                                     |
| Dimensional Tolerances                                  |            | TLMA                                    |
| Compressive Strength unit category                      |            | II                                      |
| Mean compressive strength, N/mm <sup>2</sup>            |            | 2.9                                     |
| Dimensional stability (shrinkage), mm/m                 |            | 0.4                                     |
| Shear bond strength, N/mm²                              |            | 0.15 with GPLM                          |
|   |            | 0.30 with TLM                           |
|   |            | (Tabulated value according to EN 998-2) |
| Reaction to fire  |            | Euroclass A1                            |
| Water absorption, g/m <sup>2</sup> s <sup>0,5</sup>     |            | NPD                                     |
| Water vapour diffusion coefficient μ                    |            | 5/10                                    |
|   |            | (Tabulated value according to EN1745)   |
| Durability (freeze-thaw resistance)                     |            | For use above and below ground level    |
| Gross dry bulk density, mean, kg/m <sup>3</sup>         |            | 460                                     |
| Form and shape  |            | Solid Group 1                           |
| Thermal conductivity, λ <sub>10,dry</sub> (P=50%), W/mK |            | 0.10                                    |

9. The performance of the product identified above is in conformity with the declared performance.

This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, as it has effect in the United Kingdom under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of H+H UK Limited

Calm J Fasyth

Calum Forsyth (Managing Director)

Borough Green, Kent

12 May 2021

Document Version: - 01: First issue





H+H UK Ltd, Celcon House, Ightham, Sevenoaks, Kent, TN15 9HZ

21

UKCA - UGP140 - 01

BS EN 771-4:2011 + A1:2015

## **Solar Grade Celcon Plus Blocks**

Load bearing and non-load bearing applications in all forms of walling including single leaf, cavity, partitions, retaining and basements

Category II, autoclaved aerated concrete masonry unit

**Dimensions:** (Length x Height x Width) 630mm x 215mm x 140mm

**Dimensional tolerances:** Category: TLMA

**Configuration:** Solid (Group 1 unit to EN1996-1-1)

Compressive strength: Mean 2.9 N/mm² (⊥ bedface, whole unit) (Cat II)

**Dimension stability:** Moisture movement: 0.4 mm/m

Bond strength (initial shear): Fixed Value 0.15 N/mm² with GPLM

0.30 N/mm<sup>2</sup> with TLM

Flexural Bond strength: NPD

Reaction to fire: Euroclass A1

Water absorption: NPD

Water vapour diffusion coefficient: Fixed Value 5/10

Gross density: 460 kg/m<sup>3</sup>

Thermal conductivity: 0.10 W/mK  $(\lambda_{10,dry})$ 

**Durability:** For use above and below ground level